

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk

9630

TEST CERTIFICATE

CLIENT:	Texdecor SAS 2 Rue D'Hem FR-59780 Willems - - - -	Certificate Number:	UK2201720 -1
		Date Received:	28/07/2022
		Date Issued:	12/12/2022
		Issue Number:	2
		Changes made from previous issue (if applicable)	
Contact:	-	Composition name change	
Tel:	-		
Email:	-		

SAMPLE IDENTIFICATION

The information in this section is provided by the client and Lancashire Testing Services Ltd assumes no responsibility or liability for its accuracy.

Sample Name / Reference	Notte 3775
Additional Names:	-
Batch Ref/Number:	-
Order Number:	20220722A
Colour:	01/
Fabric Composition:	100% PES fac fabric + 4 pass Flock FR Coating
Customer:	-

SPECIFICATION

BS5867-2:2008 Fabrics for curtains, drapes and window blinds

Type B

TEST METHOD

Flammability: BS EN ISO 15025:2002 - Procedure A -Surface Ignition

Pre-treatment: None Requested

-

ConclusionThe sample tested: **Complies** with the flammability requirements of:

BS5867-2:2008 Type B As supplied

Taking into account uncertainty of measurement

Measurements of uncertainty: Time ± 1 second, Dimension ± 1 mm

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk

9630

TEST CERTIFICATE**Test Results:-****BS5867-2:2008 Fabrics for curtains, drapes and window blinds****Type B**

"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use."

Sample Code	UK2201720 -1					
Sample Name / Reference	Notte 3775					
Client	Texdecor SAS					
Date of test	03/08/2022					
Pre-Treatment	None requested -					
Test Conditions	Period h	Temperature °C		Relative humidity %	Air Flow m/s	Volume m ³
Conditioning of test specimens	≥24	20±2		65±5	-	-
Testing conditions	-	10-30		15-80	≤0.2	≥4
Flame Application time	15 second Face burn			Flame Height (vertical)		40 ± 2mm
Sample size	200 x 160mm			Fabric face tested		Outer
Longest Dimension	Machine Direction			Cross Direction		
As Supplied	1↑	2↓	3↑	4→	5←	6→
Duration of Afterflame (s)	0	0	0	0	0	0
Duration of Afterglow (s)	1	2	1	1	2	1
Flame reached an edge	NO	NO	NO	NO	NO	NO
Hole reached an edge	NO	NO	NO	NO	NO	NO
Flaming Debris	NO	NO	NO	NO	NO	NO
Damage length Horizontal (mm)	17	18	18	14	14	16
Damage length Vertical (mm)	61	58	62	50	55	50
RESULT:	PASS					

After Wash Procedures	1↑	2↓	3↑	4→	5←	6→
Flame reached an edge	-	-	-	-	-	-
Hole reached an edge	-	-	-	-	-	-
Flame reached an edge	-	-	-	-	-	-
Hole reached an edge	-	-	-	-	-	-
Flaming Debris	-	-	-	-	-	-
Damage length Horizontal (mm)	-	-	-	-	-	-
Damage length Vertical (mm)	-	-	-	-	-	-
RESULT:	-					
Deviation from specified procedure:	-					

Please note that copies of this original certificate are not valid

Issue Number: 2

**LANCASHIRE TESTING SERVICES LIMITED**

Lyon Road Industrial Estate : Kearsley : Bolton

Lancashire : BL4 8NB

Tel: +44 (0) 1204 792858

Email: enquiries@ltslab.co.uk

www.ltslab.co.uk

9630

Craig Allardice Laboratory Technician	Tony Alcock Laboratory Technician	John Marsh Laboratory Supervisor	Peter Collings Operations Manager

Decision Rule:

Lancashire Testing Services have measurement uncertainties for all test standards (available on request) and have applied these measurements to the test result.

The specific level of risk is < 2.5% as stated in ILAC-G8:09/2019. Unless otherwise indicated L.T.S will apply this rule to all measurements reported.

If the measurement result plus/minus the expanded uncertainty with a 95 % coverage probability overlaps the limit, it is not possible to state compliance or non-compliance. The measurement result and the expanded uncertainty with a 95 % coverage probability will then be reported. The report will include the actual value with the uncertainty range.

Lancashire Testing Services Ltd have conducted thorough analysis of the uncertainty of all measurements carried out in the application of the standard or standards detailed in this report. Where possible any associated uncertainty of measurements have been accounted for in the working instructions, so that they have no impact on the reporting of the final result. In instances where uncertainty of measurements can only be taken into account after the test has been conducted, these uncertainty values have been stated on this report. The stated uncertainty of measurement has also been taken into account in the final reporting of the overall result.

Information provided about a customer, from a source other than the customer, shall only be shared with the customer. The provider of the information shall remain confidential to the laboratory unless agreed by the source of the information.

Please note that copies of this original certificate are not valid

Issue Number: 2